



**University of
Zurich**^{UZH}

**Zurich Open Repository and
Archive**

University of Zurich
University Library
Strickhofstrasse 39
CH-8057 Zurich
www.zora.uzh.ch

Year: 2013

Structure and magnetic interactions in the solid solution $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$

Grundmann, Henrik ; Schilling, Andreas ; Marjerrison, Casey A ; Dabkowska, Hanna A ; Gaulin, Bruce D

Abstract: Solid solutions of the magnetic insulators $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$ ($\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$) have been prepared in polycrystalline form for the first time. Single crystalline material was obtained using a mirror image floating zone technique. X-ray diffraction data taken at room temperature indicate that the space group of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ remains unchanged for all values of x , while the cell parameters depend on the chemical composition, as expected. Magnetization data, measured from 300 K down to 2 K, suggest that the interaction constant J_d within the Cr^{5+} dimers varies in a peculiar way as a function of x , starting at $J_d = 25$ K for $x = 0$, then first slightly dropping to $J_d = 18$ K for $x = 0.75$, before reaching $J_d = 62$ K for $x = 3$.

DOI: <https://doi.org/10.1016/j.materresbull.2013.04.080>

Posted at the Zurich Open Repository and Archive, University of Zurich

ZORA URL: <https://doi.org/10.5167/uzh-92198>

Journal Article

Accepted Version

Originally published at:

Grundmann, Henrik; Schilling, Andreas; Marjerrison, Casey A; Dabkowska, Hanna A; Gaulin, Bruce D (2013). Structure and magnetic interactions in the solid solution $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$. *Materials Research Bulletin*, 48(9):3108-3111.

DOI: <https://doi.org/10.1016/j.materresbull.2013.04.080>

Structure and magnetic interactions in the solid solution $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$

Henrik Grundmann^{a,*}, Andreas Schilling^a, Casey A. Marjerrison^b, Hanna A. Dabkowska^c, Bruce D. Gaulin^{b,c,d}

^a*Universität Zürich, Physik-Institut, Winterthurerstr. 190, CH-8057 Zürich, Switzerland*

^b*Department of Physics and Astronomy, McMaster University, Hamilton, Ontario, L8S 4M1, Canada*

^c*Brockhouse Institute for Materials Research, McMaster University, Hamilton, Ontario, L8S 4M1, Canada*

^d*Canadian Institute for Advanced Research, 180 Dundas Street W, Toronto, Ontario, M5G 1Z8, Canada*

Abstract

Solid solutions of the magnetic insulators $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$ ($\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$) have been prepared in polycrystalline form for the first time. Single crystalline material was obtained using a mirror image floating zone technique. X-ray diffraction data taken at room temperature indicate that the space group of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ remains unchanged for all values of x , while the cell parameters depend on the chemical composition, as expected. Magnetization data, measured from 300 K down to 2 K, suggest that the interaction constant J_d within the Cr^{5+} dimers varies in a peculiar way as a function of x , starting at $J_d = 25$ K for $x = 0$, then first slightly dropping to $J_d = 18$ K for $x \approx 0.75$, before reaching $J_d = 62$ K for $x = 3$.

Keywords: Quantum magnetism, Dimers, BEC

*Corresponding author. Tel.: ++41 44 635 5782; Fax: ++41 44 635 5704
Email address: grundmann@physik.uzh.ch (Henrik Grundmann)


1. Introduction

In the last years, many spin dimer systems have been shown to exhibit a field induced phase transition of the magnetic subsystem [1, 2] below a critical temperature and above a certain critical magnetic field H_c . This phenomenon has been interpreted in terms of a Bose-Einstein condensation (BEC) of the magnetic quasiparticles (triplons) in connection with the collective dimer states[3].

The materials $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$ are examples for such spin dimer systems, and they have been considered as possible candidates for a triplon BEC [4, 5, 6, 7, 8, 9, 10, 11]. Recently, these two compounds have been proposed as candidates for a new experimental scheme to probe the macroscopic phase coherence that should be found in all Bose-Einstein condensates [12]. It has been argued that compounds in a solid solution of $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$ might have different critical fields than the mother compounds, but with otherwise similar physical properties. The chemical potential μ for the triplon quasiparticles in such materials is controlled by the external magnetic field H through $\mu = g\mu_B\mu_0(H - H_c)$ [13] with μ_B the Bohr magneton and g the Landé factor. A change in the chemical potential stemming from, e.g., a changed stoichiometry leading to slightly differing values for H_c between two compounds, might induce Josephson effects in a device of two of such crystals coupled together[12]. We therefore systematically studied the system $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ to obtain information about its physical properties, in particular about the magnetic interaction constants that determine the value of the critical fields H_c .

2. Experimental details

The samples were first synthesized as polycrystalline powders using standard solid-state reaction schemes. We used three different methods to prepare the polycrystalline material. First, $\text{Ba}(\text{NO}_3)_2$, $\text{Sr}(\text{NO}_3)_2$ and $\text{Cr}(\text{NO}_3)_2 \cdot 9\text{H}_2\text{O}$ were used as reactants. The powders were mixed according to



dissolved in water and heated afterwards while continuously stirred to keep the mixture homogeneous. After evaporating the water, the remaining powder was ground and heated under flowing argon at 915°C for 24 h to remove any excess water and NO_x . The resulting oxide powder was ground again, mechanically pressed into pellets and sintered at 1100°C for 48 h under flowing Ar. For $x = 0.1$ and $x = 1.5$, rods were hydrostatically pressed and annealed under the same conditions. The obtained polycrystalline material was black. An optical floating zone method was used to grow crystals from those rods [14]. Two of the resulting polycrystalline rods were then mounted in a *Crystal Systems Inc.* image furnace using Pt wire, a short one (about 3 cm) as a seed rod, and a longer one (about 10 cm) as a feed rod. The crystal growth was performed in two stages, both in a high-purity environment of flowing Ar. The first stage was performed relatively fast (growth rates between 21 mm/h and 25 mm/h) to produce a premelted rod with a high density. For the second stage, the premelted rod was used as a feed rod with the remnants of the former feed rod as a seed. The growth rate was relatively low (between 2 mm/h and 5 mm/h), but was varied during the growth





Figure 1: X-ray Laue diffractogram for the grown boule of $\text{Ba}_{2.9}\text{Sr}_{0.1}\text{Cr}_2\text{O}_8$. The beam direction was close to the c -axis. The hexagonal symmetry is clearly visible.


to maintain the zone stability. The resulting boule consisted of several, well oriented grains (see Fig. 1 for the X-ray Laue-diffractogram).

While we obtained crystalline samples for $x = 0.1$, attempts with $x = 1.5$ have not yet resulted in crystalline material.

Additionally, polycrystalline samples of several stoichiometries were prepared according to



and



The respective carbonates and chromium oxides were mixed, ground and heated under flowing argon at 1000 °C for 24 h. The resulting material was

ground again and sealed in an alumina crucible inside a quartz tube under vacuum to prevent a reaction between sample and tube. The tube was heated up to 1200 °C for 24 h and quenched into water. This last step was repeated several times, with intermediate grindings. Each of the three preparation methods yielded homogeneous black polycrystalline material and we did not find relevant differences between the respective products for any value of x between 0 and 3. However, we noted that grinding the material again thoroughly in air or dry He-atmosphere led to a slightly green color of the ground powder for every value of x .

The results shown below were obtained from the samples prepared by the first method described above, and from single crystalline material (for $\text{Ba}_{2.9}\text{Sr}_{0.1}\text{Cr}_2\text{O}_8$).

3. Crystallographic structure

In order to perform structural analysis, parts of the boule as well as corresponding polycrystalline samples with $0 \leq x \leq 3$ were ground and examined using $\text{Cu}_{K\alpha}$ X-ray radiation. The resulting patterns were analyzed using the Rietveld method (*FullProf suite*). As expected, no difference was found between ground single crystals and polycrystalline material. All of the observed reflections of the mixed crystals are in good agreement with the space group $R\bar{3}m$ (see Fig. 2), which is the same as that of the mother compounds with $x = 0$ and $x = 3$. As scattering coefficients for Cr^{5+} were not available, we used the known values for Cr^{3+} . The absolute values of the cell parameters depend linearly on the strontium content x , in agreement with Vegard's law (see Fig. 3). In Fig. 5, we have plotted the distance between two Cr ions forming a single dimer. As expected, this intradimer distance also decreases

smoothly as a function of x . We did not find any relevant systematic change in the relative atomic positions as a function of x , although it should be noted that the sensitivity on the oxygen position is not high enough to exclude such a shift. In Fig. 4, we show the z -value of the atomic position for the Cr and Ba/Sr ions while the respective x and y coordinates were assumed to be zero. All other coordinates were kept zero for all x .




Figure 2: Experimental and calculated X-ray diffraction intensities for $\text{Ba}_{0.5}\text{Sr}_{2.5}\text{Cr}_2\text{O}_8$

4. Magnetic properties

The magnetic properties of the polycrystalline samples were analyzed using a commercial SQUID magnetometer (*Quantum Design Inc.*). The magnetization was measured for temperatures between 5 K and 300 K and in magnetic fields of $\mu_0 H = 1$ T and $\mu_0 H = 5$ T. For compositions with $x < 0.2$ and $x > 2.8$, the magnetization shows a pronounced maximum at




Figure 3: Lattice constants $a = b$ and c of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ as obtained from X-ray diffraction data, as functions of the strontium content x .

low temperatures. The experimental data can be well described with the Bleaney-Bowers formula for interacting dimers,

$$M_d(T) = \frac{n_d g^2 \mu_B B_{\text{ext}}}{J_e + k_B T \left(3 + e^{\frac{J_d}{k_B T}} \right)}, \quad (1)$$

with $g = 1.94$ which is only slightly anisotropic in these systems[15, 16], n_d the density of the coupled ions and J_e and J_d the inter- and intradimer coupling constants, respectively. For intermediate values of x around 1.5, a paramagnetic background becomes more and more relevant so that a Brillouin term had to be included,

$$M_p(T) = n_P g \mu_B \frac{1}{2} \left(2 \coth \left(\frac{g \mu_B B_{\text{ext}}}{k_B T} \right) - \coth \left(\frac{g \mu_B B_{\text{ext}}}{2 k_B T} \right) \right), \quad (2)$$

where n_P denotes the density of the corresponding uncoupled ions. The experimental data are reasonably well described by the sum of the above




Figure 4: z -value of the atomic position for the Cr (circles) and Ba₂/Sr₂(nomenclature according to [15]) (diamonds) ions as a function of the strontium content x . The x - and y -values were kept at zero.




Figure 5: Distance between the Cr ion constituting one dimer as a function of the strontium content x .

terms (see Fig. 6). However, as the fit is not very sensitive to the interdimer interaction constant J_e (especially in the presence of a strong paramagnetic background) we could not extract reliable values for it.

The thus obtained intradimer interaction constant J_d strongly depends on the stoichiometry, as shown in Fig. 7. Surprisingly, it first decreases with increasing strontium content up to $x \approx 1$, before increasing again up to the value for pure $\text{Sr}_3\text{Cr}_2\text{O}_8$. As the relative atomic positions do not change with x (see Fig. 4), we attribute the overall increase of the interaction constant to a decrease of the absolute intradimer distance of the Cr^{5+} -ions from pure $\text{Ba}_3\text{Cr}_2\text{O}_8$ to pure $\text{Sr}_3\text{Cr}_2\text{O}_8$ (see Fig. 5). As a consequence, the variation of J_d with x should lead to an associated change in the critical field H_c , which we will investigate in a separate report.

In Fig. 7 we also show the fraction n_d of dimerized Cr^{5+} ions and we compare it in Fig. 8 with the density n_p of uncoupled Cr^{5+} ions, both treated as independent fitting parameters. The paramagnetic background for intermediate x is substantial, but its microscopic origin is not clear up to now. The sum of the prefactors n_d and n_p is reasonably close to 1, which supports the validity of our fitting procedure. An increase of the preparation temperature to 1250°C as well as repeated grinding and annealing of the polycrystalline samples did not reduce this background contribution substantially, but our corresponding X-ray diffraction data do, most interestingly, not suggest the appearance of possible impurity phases. In Fig. 9 we show the part of the total scattering intensity that is neither associated with the expected diffraction peaks of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ ($I_{\text{calc.}}$) nor with the diffuse background ($I_{\text{diff.}}$), normalized to the total integrated intensity without the diffuse background.




Figure 6: Upper panel: magnetization data $\frac{m}{B}(T)$ for four different stoichiometries of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ in $\mu_0 H = 1$ T. The solid lines correspond to fits according to a sum of Eqs. 1 and 2. The lower panels show the respective extracted paramagnetic (par.) and dimer (dim.) contributions to the total magnetization.




Figure 7: Estimated intradimer interaction constant J_d in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ (filled circles) and the fraction of dimerized Cr^{5+} -ions (crosses, prefactor n_d from Eq. 1), as a function of the strontium content x .




Figure 8: Estimated fraction n_d of dimerized (crosses) and free Cr^{5+} -ions n_p (plus signs) from Eqs. 1 and 2 and the sum $n_d + n_p$ (stars), as functions of the strontium content x .

Within the accuracy of this procedure, diffraction peaks stemming from unwanted impurity phases are virtually absent for all values of x . We therefore believe that this magnetic background is intrinsic to the polycrystalline system $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$.




Figure 9: Integrated scattering intensity of potential impurities.

5. Conclusion

We have for the first time synthesized mixed crystals of the magnetic insulators $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$. The structure of the solid solution series remains unchanged, but with linearly decreasing cell parameters for increasing Sr-content x . The magnetic behavior indicates the presence of a dimerized spin system for all values of x , with an interaction constant J_d that strongly depends on the composition and surprisingly falls below the value of pure $\text{Ba}_3\text{Cr}_2\text{O}_8$ in certain range of x . For intermediate values ($x \approx 0.5 \dots 2.0$),

a paramagnetic background appears that does not seem to be related to impurity phases and is therefore probably intrinsic to $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$.

6. Acknowledgements

We would like to thank Dr. M. Medarde Barragan and Dr. A. Krzton-Maziopa for valuable discussions. We also would like to thank T. Munsie and Antoni B. Dabkowski for their help in the crystal growth and characterization. This work was supported by the Swiss National Science Foundation Grants No. 21-126411 and 21-140465.

References

- [1] W. Shiramura, K. Takatsu, H. Tanaka, K. Kamishima, M. Takahashi, H. Mitamura, T. Goto, Journal of the Physical Society of Japan 66 (1997) 1900.
- [2] M. Jaime, V. F. Correa, N. Harrison, C. D. Batista, N. Kawashima, Y. Kazuma, G. A. Jorge, R. Stern, I. Heinmaa, S. A. Zvyagin, Y. Sasago, K. Uchinokura, Physical Review Letters 93 (2004) 087203.
- [3] T. Nikuni, M. Oshikawa, A. Oosawa, H. Tanaka, Physical Review Letters 84 (25) (2000) 5868.
- [4] H. J. Mattausch, H. K. Müller-Buschbaum, Zeitschrift für Naturforschung B 27 (1972) 739.
- [5] E. Cuno, H. K. Müller-Buschbaum, Zeitschrift für anorganische und allgemeine Chemie 572 (1989) 95.

- [6] T. Nakajima, H. Mitamura, Y. Ueda, Journal of the Physical Society of Japan 75 (2006) 054706.
- [7] Y. Singh, D. C. Johnston, Physical Review B 76 (2007) 012407.
- [8] A. A. Aczel, Y. Kohama, M. Jaime, K. Ninios, H. B. Chan, L. Balicas, H. A. Dabkowska, G. M. Luke, Physical Review B 79 (2009) 100409.
- [9] A. A. Aczel, H. A. Dabkowska, P. R. Provencher, G. M. Luke, Journal of Crystal Growth 310 (2008) 870.
- [10] A. A. Aczel, Y. Kohama, C. Marcenat, F. Weickert, M. Jaime, O. E. Ayala-Valenzuela, R. D. McDonald, S. D. Selesnic, H. A. Dabkowska, G. M. Luke, Physical Review Letters 103 (2009) 207203.
- [11] D. Kamenskyi, J. Wosnitza, J. Krzystek, A. A. Aczel, H. A. Dabkowska, A. B. Dabkowski, G. M. Luke, S. A. S.A. Zvyagin, Journal of Low Temperature Physics 170 (2013) 231.
- [12] A. Schilling, H. Grundmann, Annals of Physics 327 (2012) 2309.
- [13] T. Giamarchi, C. Rüegg, O. Tcherniyshyov, Nature Physics 4 (2008) 198.
- [14] H. A. Dabkowska, A. B. Dabkowski, Springer Handbook of Crystal Growth, Defects and Characterization, Springer Berlin Heidelberg, 2010, Ch. 12, pp. 367–391.
- [15] M. Kofu, H. Ueda, H. Nojiri, Y. Oshima, T. Zenmoto, K. C. Rule, S. Gerischer, B. Lake, C. D. Batista, Y. Ueda, S.-H. Lee, Physical Review Letters 102 (2009) 177204.

- [16] D. L. Quintero-Castro, B. Lake, E. M. Wheeler, A. T. M. N. Islam, T. Guidi, K. C. Rule, Z. Izaola, M. Russina, K. Kiefer, Y. Skourski, Physical Review B 81 (2010) 014415.